



United Wax Co., Ltd.
台灣中華蠟業有限公司

United Wax Co., Ltd.
Specification of Products

MR 145 (橡膠防護蠟)

<u>Property</u>	<u>Specification</u>	<u>Typical</u>	<u>Method</u>
比重 Specific gravity @250°F	—	—	ASTM D1298
熔點 Melting Point, °F	143~150°F (62~66°C)	145	ASTM D938
油含量 Oil Content, wt%	Max. 0.5	0.47	ASTM D721
針入度 Needle Penetration @77°F,	Max. 15.0	13.3	ASTM D1321
色度 ASTM Color	+25~+30	+28	ASTM D1500
Viscosity, cSPs @212 °F	4.5~5.2	4.969	ASTM D445

※ °F = °C * 1.8 + 32

※ 100°C = 212°F ; 77°F = 25°C