

TSR1452E

silicone coating and binder resin



MARKETING BULLETIN

SILANES - COATINGS ADDITIVES

TSR1452E silicone resin is a 60% by weight methyl phenyl silicone in solvent that produces a medium-hard film. Delivering exceptional heat, weather and chemical resistance, it is an excellent candidate for use as a vehicle in paint formulations.

Key Features and Typical Benefits

- Excellent thermal resistance with good gloss and color retention
- Low molecular weight polymer, enabling good compatibility with a wide range of organics
- Delivery of thermal resistance as a sole vehicle
- Improved heat resistance when blended with organic vehicles
- Extended shelf life of 18 months when stored below 25 °C

Typical Physical Properties

Property	Value
Appearance	Transparent, light yellow liquid
Specific Gravity at 25 °C	1.06
Viscosity at 25 °C, mPa·s	27
Solid Content, %	60
Diluent	Xylene / ethylbenzene

Typical properties are average data and are not to be used as or to develop specifications.

Mechanical Film Test Properties

TSR1452E silicone resin was coated on a steel sheet (SPC-1 50 mm x 50 mm x 1.0 mm thickness) with a film thickness of 30-40 µm and cured at 150 °C for one hour. The resulting physical properties of the film were evaluated as shown in the table below.

Property	Cured Film at 150 °C, 1 hour
Film Hardness (Sward rocker test)	55
Erichsen Indication, mm	4
Drawing Test	20/20 (no flaking)
Cross Cut Adhesion Test	No coating flakes
Bend Test (bent over a 3 mm in diameter mandrel)	Yes (flexible)

Note: Test results. Actual results may vary.

Gloss and Color Retention Test

A model black enamel containing TSR1452E silicone resin (as a top coat) was evaluated for gloss and color retention after exposures at 250 °C and 400 °C each for 16 hours.

Black enamel test formulation and procedures:

Ingredient	Parts by weight
TSR1452E silicone resin (100% solid resin)	140
Mica Powder (Takaramaika #103 from Takara Kogyo Co.)	70
Ceramic Black #2930 from Ferro Enamels (Japan) Ltd.	70
Stearic Acid Aluminum	0.3
Xylene	50

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

A non-treated steel sheet (SPC-1 50 mm x 50 mm x 1.0 mm in thickness) was applied with (first coat) silicone aluminum paint with 20 µm thickness and cured at 150 °C for 1 hour. The model black enamel containing TSR1452E silicone resin was then applied with 25 µm thickness and cured at 150 °C for 1 hour.

Test Condition	Black Enamel with TSR1452E Silicone Resin				Black Enamel with Standard Methyl Phenyl Resin			
	Gloss (60°)			Color Retention	Gloss (60°)			Color Retention
	Initial	After 16 hour Heat Exposure	% Gloss Retention	Delta E	Initial	After 16 hour Heat Exposure	% Gloss Retention	Delta E
250 °C for 16 hours	37.7	23.2	61.5	0.7	31.8	7.0	22.0	5.6
400 °C for 16 hours	37.1	9.1	24.5	2.7	34.5	2.7	7.8	7.0

Note: Test results. Actual results may vary.

The model black enamel formulation with TSR1452E silicone resin had excellent gloss and color retention after exposure to 250 °C for 16 hours as compared to the enamel containing a standard silicone resin.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Customer Service Centers

Worldwide

Email: commercial.services@momentive.com

Americas+1 800 295 2392
+1 614 986 2495**Europe, Middle East,
Africa and India**00800 4321 1000
+40 213 044229**Asia Pacific****China**
800 820 0202
+86 21 3860 4892**All Other Countries**
+60 3 9206 1543**Japan**0120 975 400
+81 276 20 6182

Disclaimer

FORMULATIONS ARE ILLUSTRATIVE EXAMPLES AND DO NOT REPRESENT COMMERCIALIZED PRODUCTS. They have not been subjected to extensive testing and Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the performance, efficacy or safety of any product manufactured using such formulations. EACH USER BEARS FULL RESPONSIBILITY FOR (1) MAKING ITS OWN DETERMINATION AS TO THE SUITABILITY AND LEGAL COMPLIANCE OF ANY FORMULATION, MATERIALS, RECOMMENDATIONS, OR ADVICE FOR ITS OWN PARTICULAR USE, (2) IDENTIFYING AND PERFORMING ALL TESTS AND ANALYSES NECESSARY TO ASSURE THAT ITS FINISHED PRODUCTS BASED UPON EXAMPLE FORMULATIONS AND/OR INCORPORATING MENTIONED PRODUCTS, MATERIALS, OR SERVICES WILL BE SAFE AND SUITABLE FOR USE UNDER END-USE CONDITIONS, AND (3) OBTAINING ANY NECESSARY GOVERNMENT OR REGULATORY CLEARANCE, LICENSE OR REGISTRATION.

Any reference to a third party's materials is not an endorsement of those materials or an endorsement by the third party of Momentive materials. Momentive has not undertaken a comprehensive patent or other intellectual property search on the formulations. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

BEFORE HANDLING ANY PRODUCTS MENTIONED, REVIEW THE LATEST SAFETY DATA SHEET (SDS) AND LABEL FOR PRODUCT SAFETY INFORMATION, SAFE HANDLING INSTRUCTIONS, PERSONAL PROTECTIVE EQUIPMENT IF NECESSARY, EMERGENCY SERVICE CONTACT INFORMATION, AND ANY SPECIAL STORAGE CONDITIONS REQUIRED FOR SAFETY. MOMENTIVE MAINTAINS AN AROUND-THE-CLOCK EMERGENCY SERVICE FOR ITS PRODUCTS. SDS FOR MOMENTIVE PRODUCTS ARE AVAILABLE AT WWW.MOMENTIVE.COM OR, UPON REQUEST, FROM ANY MOMENTIVE REPRESENTATIVE. USE OF OTHER MATERIALS IN CONJUNCTION WITH MOMENTIVE PRODUCTS MAY REQUIRE ADDITIONAL PRECAUTIONS. PLEASE REVIEW AND FOLLOW THE SAFETY INFORMATION PROVIDED BY THE MANUFACTURER OF SUCH OTHER MATERIALS.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier.